

- +44 (0)1928 599910
- sales@aquabond.co.uk
- Unit 5a Christleton Court Manor Park, Runcorn Cheshire, WA7 1ST

Product Data Sheet: Sandtex

<u>General</u>

Sandtex is a matt clear embossed PVC over laminating film exhibiting minimal glare and coated with a permanent acrylic adhesive suitable for over lamination of all ink types including UV inks.

The rough textured light diffusing finish gives excellent anti-scuff and anti-slip properties and therefore this product is commonly used for floor graphics (industry tested and approved), pop-up displays and general paper and filmic poster graphic over lamination.

Product is suitable for

- Short to Mid Term Application
 - *Product durability and adhesion is guaranteed for 6 months for indoor applications as a matching system, when product is used in conjunction with Aquabond AB100-300 range of monomeric vinyl*
- Indoor Use
- POP displays
- Wall Graphics
- Over lamination of Floor Graphics

Product Benefits are

- Excellent light diffusion
- Good abrasion/scuff resistance
- Slip Resistant
- Fire Resistant

Standard Width: 880mm; 1040mm; 1300mm; 1370mm,1530mm

Product Features and Performance Data.

Face Material	Sand Textured Matt Clear Embossed Monomeric PVC	100 μm ± 10
Adhesive	Acrylic water based permanent PSA	28 μm ± 2
Liner	White, Kraft, PE coated 1 side siliconized	80 µm ± 8
Application temperature		10°C to 40°C
Shelf Life	Year if stored in original packaging free from moisture and excessive exposure to ultra violet radiation	
Slip Test	Dry: Low Risk Wet: Low Risk	BS7976-2
	R9	DIN51130.2014
Fire Test	Class 0	BS476 part 6&7

NB When applied as an over lamination film for floor graphic applications it is recommended that radius cut corners are used.

This information is given as a guideline and due to the wide variation in surface to which this product may be applied the end user MUST carry out suitable testing to satisfy themselves as to satisfactory performance

^{*}Due to the wide variation in potential surfaces Aquabond cannot accept any responsibility for the adhesive performance in the event of adhesion failure*